



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>B29C 55/18</b>		A1	(11) International Publication Number: <b>WO 98/51475</b>
			(43) International Publication Date: 19 November 1998 (19.11.98)
(21) International Application Number: PCT/IB98/00663 (22) International Filing Date: 1 May 1998 (01.05.98) (30) Priority Data: 08/853,301                      9 May 1997 (09.05.97)                      US (71) Applicant: THE PROCTER & GAMBLE COMPANY [US/US]; One Procter & Gamble Plaza, Cincinnati, OH 45202 (US). (72) Inventors: DOBRIN, George, Christopher; 2941 Eggers Place, Cincinnati, OH 45211 (US). GOENS, Thomas, Masazi; 4123 Lora Avenue, Cincinnati, OH 45211 (US). PHILLIPS, Donna, Sue; 7717 North Hogan Road, Aurora, IN 47001 (US). CURRO, John, Joseph; 3102 Dot Drive, Cincinnati, OH 45213 (US). (74) Agents: REED, T., David et al.; The Procter & Gamble Company, 5299 Spring Grove Avenue, Cincinnati, OH 45217 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  Published With international search report.	
(54) Title: METHOD FOR FORMING A BREATHABLE FILM			
(57) Abstract			
<p>A film (12) which is a blend of a thermoplastic polymer and an inorganic filler is fed between a first roll (52) and a second roll (54). The first roll has a plurality of toothed regions (56) spaced apart by a plurality of grooved regions (58). The toothed regions include a plurality of teeth (57). The second roll has a plurality of teeth (61) which mesh with the teeth on the first roll. As the film is fed between the first roll and the second roll the portion of the film passing between the grooved regions on the first roll and the teeth on the second roll remains substantially planar forming first regions (64) in the film while the portion of the film passing between the teeth on the first roll and the teeth on the second roll are formed into second regions (66) having raised rib-like elements.</p>			

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## METHOD FOR FORMING A BREATHABLE FILM

5

### FIELD OF THE INVENTION

The present invention relates to a method for forming a breathable film, and  
10 more particularly, to a method for forming a breathable film comprising a blend of a  
thermoplastic polymer with an inorganic material. The breathable film is particularly  
useful as a backsheet on a disposable absorbent article.

### BACKGROUND OF THE INVENTION

15 Infants and other incontinent individuals wear disposable absorbent articles such  
as diapers to receive and contain urine and other body exudates. Absorbent articles  
function both to contain the discharged materials and to isolate these materials from the  
body of the wearer and from the wearer's garments and bed clothing. Disposable  
absorbent articles having many different basic designs are known to the art. It is also  
20 known that the exterior of disposable diapers can be covered with a flexible, liquid and  
vapor impervious sheet to prevent any absorbed liquid from passing through the diaper  
and soiling adjacent articles such as clothing, bedding and the like. These outer covers,  
generally referred to as backsheets, are often constructed from fluid impervious films  
such as polyethylene. Although such backsheets do prevent liquid from passing  
25 through the diaper, they also can make the diaper feel hot and uncomfortable to wear  
because of their impermeability to air and/or moisture.

Backsheets which are pervious to vapor are generally known as breathable  
backsheets and have been described in the art. In general, these backsheets are  
intended to allow the passage of vapor through them while retarding the passage of  
30 liquid. For example, U.S. Pat. No. 3,156,342 issued to Crowe, Jr. on November 10,  
1964 teaches the use of a microporous film as a breathable backsheet. U.S. Pat. No.  
3,881,489 issued to Hartwell on May 6, 1975 teaches a breathable backsheet  
comprising in combination two layers, the first of which is a low void volume  
perforated thermoplastic film and the second of which is a porous high void volume  
35 hydrophobic tissue. U.S. Pat. No. 3,989,86 issued to Sisson on November 2, 1976  
teaches a breathable backsheet provided with tapered hollow bosses which prevent the  
passage of liquids while allowing vapors to readily pass.

Of the breathable backsheets, microporous films are most commonly used. Microporous films typically comprise a blend of a thermoplastic polymer and an inorganic filler such as calcium carbonate. The blend undergoes pore formation upon stretching as the inorganic filler separates from the polymer due to stress concentration.  
5 The formation of micropores permits the film to be breathable allowing the passage of vapor through the micropores while retarding the passage of liquid.

It is an object of the present invention to provide a novel process for forming a breathable film from a blend of a thermoplastic polymer with an inorganic material.

10

### **SUMMARY OF THE INVENTION**

In accordance with the present invention, there is provided a method for forming a breathable film. The film is comprised of a blend of a thermoplastic polymer with an inorganic material being selected from the group consisting of calcium carbonate, clay and titanium dioxide, with the preferred inorganic filler being  
15 calcium carbonate. The blended film is fed between a pair of opposing first and second rolls. The first roll comprises a plurality of toothed regions spaced apart by a plurality of grooved regions wherein the toothed regions comprises a plurality of teeth. The second roll comprises a plurality of teeth which mesh with the teeth on the first roll. As the film is fed between the first and said second rolls the portion of the  
20 film passing between the grooved regions on the first roll and the teeth on the second roll remains substantially planar forming a first region in the film while the portion of the film passing between the teeth on the first roll and the teeth on the second roll is formed into second regions having raised rib-like elements.

25

### **BRIEF DESCRIPTION OF THE DRAWINGS**

While the specification concludes with claims particularly pointing out and distinctly claiming the present invention, it is believed that the present invention will be better understood from the following description in conjunction with the accompanying drawings, in which like reference numerals identify like elements and wherein:

30 Fig. 1 is a schematic illustration of an exemplary process for forming the breathable film of the present invention;

Fig. 2 is an enlarged illustration of the opposing pairs of rolls of the process of Fig. 1;

35 Fig. 3 is a plan view illustration of a preferred embodiment of a breathable polymeric film having a first region and a second region of the present invention with the rib-like elements of the second region facing toward the viewer;

Fig. 3A is a segmented, perspective illustration of the breathable film of Fig. 3 in an untensioned condition;

Fig. 4 is an enlarged photograph of the breathable film of the present invention;

Figs. 4A and 4B are enlarged photographs of the breathable films cross-section illustrating the formation of micropores in the portions of the film which have been stretched or thinned;

Fig. 5 is an illustration of an alternative embodiment of the opposing pairs of rolls of the process of Fig. 1;

Fig. 6 is an illustration of another embodiment of the opposing pairs of rolls of the process of Fig. 1; and

Fig. 7 is a schematic illustration of an alternative process for forming the breathable film of the present invention.

#### **DETAILED DESCRIPTION OF THE INVENTION**

While the present invention will be described in the context of a method for producing a breathable film which is particularly well suited for use as a backsheet on a disposable absorbent article such as a disposable diaper, sanitary napkin, or bandage the present invention is in no way limited to such application. The detailed description of the method herein will allow one skilled in the art to readily adapt the present invention to other applications.

Referring to Fig. 1 there is schematically illustrated at 10 a process for forming a breathable material of the present invention. According to the present invention, a film 12 is unwound from supply roll 11 and travels in the direction indicated by the arrows associated therewith as the supply roll 11 rotates in the direction indicated by the arrows associated therewith. The film 12 comprises a blend of a thermoplastic polymer with an inorganic material. Suitable thermoplastic polymers include polyolefins such as polyethylenes, including linear low density polyethylene (LLDPE), low density polyethylene (LDPE), ultra low density polyethylene (ULDPE), high density polyethylene (HDPE), or polypropylene and blends thereof with the above and other materials. Examples of other suitable thermoplastic polymers which may also be used include, but are not limited to, polyester, polyurethanes, compostable or biodegradable polymers, heat shrink polymers, thermoplastic elastomers, and metallocene catalyst-based polymers (e.g., INSITE® available from Dow Chemical Company and Exxact® available from Exxon).

The inorganic material or filler is selected from the group consisting of calcium carbonate, clay and titanium dioxide, with the preferred inorganic filler being calcium carbonate. Inorganic fillers having a particle size of from about 1 to about 5 microns

and constitute of from about 5 to about 70 percent by weight of the blend, preferably from about 20 to about 60 percent by weight of the blend. The inorganic filler may be coated with a fatty acid ester to obtain higher loadings in the polymer.

The inorganic filler and the thermoplastic polymer are blended together to form  
5 a homogeneous mixture in a suitable mixing extruder, or in a separate preliminary compounding step. The mixture is then cast or blown into a film.

From the supply roll 11 the film 12 is fed through a nip 51 of a pair of opposing rolls 52 and 54 of apparatus 50. The apparatus 50 is more clearly shown in Fig. 2. Roll 52 comprises a plurality of toothed regions 56 and grooved regions 58 extending  
10 about the circumference of the roll. The toothed regions 56 include a plurality of teeth 57. Teeth 57 are substantially parallel to the axis of roll 52. Roll 54 comprises a plurality of toothed regions 60 and grooved regions 62 extending about the circumference of the roll. The toothed regions 60 include a plurality of teeth 61. Teeth 61 are substantially parallel to the axis of roll 54. The grooved regions 58 of roll  
15 52 are aligned with the grooved regions 62 of roll 54. Similarly, the toothed regions 56 of roll 52 are aligned with the toothed regions 60 of roll 54 permitting teeth 57 of roll 52 to engage or intermesh with teeth 61 of roll 54. The portions of the film 12 passing between the grooved regions 58 and 62 will be unformed, i.e., the film 12 will not be formed or stretched and will remain substantially planar, while the portions of  
20 the film passing between toothed regions 56 and 60 will be formed and/or stretched producing rib-like elements in the film.

Conventional drive means and other conventional devices which may be utilized in conjunction with the apparatus of Fig. 1 are well known and, for purposes of clarity, have not been illustrated in the schematic view of Fig. 1.

25 The above sequence may be repeated any number of times until the desired properties are obtained. Furthermore, the degree of engagement of opposing rolls, the dimension, shape and spacing of the teeth on the opposing rolls, and the size of the rolls can be chosen to produce the desired properties.

Referring now to Fig. 3 there is illustrated a preferred embodiment of a  
30 breathable film 12 after having passed through the pair of opposing rolls 52 and 54 of apparatus 50. The breathable film 12 is shown in Fig. 3 in its substantially untensioned condition. The breathable film 12 is particularly well suited for use as a backsheet on an absorbent article, such as a sanitary napkin or a disposable diaper. The film 12 has two centerlines, a longitudinal centerline, which is also referred to hereinafter as an  
35 axis, line, or direction "l" and a transverse or lateral centerline, which is also referred to hereinafter as an axis, line, or direction "t". The transverse centerline "t" is generally perpendicular to the longitudinal centerline "l".

Referring now to Figs. 3 and 3A, film 12 includes a network of distinct regions. The network includes at least a first region 64 and a second region 66. Film 12 includes a transitional region 65 which is at the interface between the first region 64 and the second region 66. Film 12 has a first surface 52a and an opposing second surface 52b. In the embodiment shown in Figs. 3 and 3A, the film includes a plurality of first regions 64 and a plurality of second regions 66. The first regions 64 have a first axis 68 and a second axis 69, wherein the first axis 68 is preferably longer than the second axis 69. The first axis 68 of the first region 64 is substantially parallel to the longitudinal axis of the film 12 while the second axis 69 is substantially parallel to the transverse axis of the film 12. The second regions 66 have a first axis 70 and a second axis 71. The first axis 70 is substantially parallel to the longitudinal axis of the film 12, while the second axis 71 is substantially parallel to the transverse axis of the film 12. In the preferred embodiment of Fig. 3, the first regions 64 and the second regions 66 are substantially linear, extending continuously in a direction substantially parallel to the longitudinal axis of the film 12.

The film 12 is comprised of at least a first region and a second region, wherein the first region is visually distinct from the second region. As used herein, the term "visually distinct" refers to features of the film which are readily discernible to the normal naked eye when the film or objects embodying the film are subjected to normal use.

In the preferred embodiment shown in Figs. 3 and 3A, the first regions 64 are substantially planar. That is, the material within the first region 64 is in substantially the same condition before and after the formation step undergone by film 12. The second regions 66 include a plurality of raised rib-like elements 74. The rib-like elements 74 have a first or major axis 76 which is substantially parallel to the transverse axis of the film 12 and a second or minor axis 77 which is substantially parallel to the longitudinal axis of the film 12. The first axis 76 of the rib-like elements 74 is at least equal to, and preferably longer than the second axis 77. Preferably, the ratio of the first axis 76 to the second axis 77 is at least about 1:1 or greater, and more preferably at least about 2:1 or greater.

The rib-like elements 74 in the second region 66 may be separated from one another by unformed areas. Preferably, the rib-like elements 74 are adjacent one another and are separated by an unformed area of less than 0.10 inches as measured perpendicular to the major axis 76 of the rib-like elements 74, and more preferably, the rib-like elements 74 are contiguous having no unformed areas between them. The dimension of the rib-like elements can also be varied. A more detailed description of a film having first and second regions as shown in Figs. 3 and 3A can be found in U.S.

Pat. No. 5,518,801 issued to Chappell et al. on May 21, 1996 which is incorporated herein by reference.

Referring now to Fig. 4 there is shown an enlarged photograph of the film 12 after having passed through a pair of opposing rolls of the present invention, like opposing rolls 52 and 54 of apparatus 50. As can be seen in Fig. 4, the film 12 includes substantially planar first regions 64 and second regions 66 which include raised rib-like elements 74. The portions of the film 12 forming the rib-like elements 74 of the second region 66 have been stretched or thinned as opposed to the thicker first regions 64 which have not been stretched or thinned. While the second regions 66 have been stretched or thinned, the stretching or thinning is not necessarily uniform throughout the second regions 66.

Figs. 4A and 4B are enlarged photographs of portions of the films cross-section. The portion of the film in Fig. 4A has been stretched to a greater degree than the portion of the film in Fig. 4B and as a result has a thickness dimension less than that of the portion of the film in Fig. 4B. In addition to having a reduced thickness, the film shown in Fig. 4A has an increased pore volume compared to the film shown in Fig. 4B. The stretching of the film separates the inorganic filler from the polymer due to stress concentration creating pores in the film. The formation of micropores permits the film to be breathable allowing the passage of vapor therethrough while retarding the passage of liquid.

One measurement of breathability is the moisture vapor transmission rate (MVTR) of the material. In order to reduce humidity and heat buildup within the diaper, it has been found that the breathable film of the present invention when used as a backsheet on a disposable diaper should have a moisture vapor transmission rate of from about 500 g/m<sup>2</sup>/24 hr. to about 5000 g/m<sup>2</sup>/24 hr., more preferably from about 1000 g/m<sup>2</sup>/24 hr. to about 5000 g/m<sup>2</sup>/24 hr., and most preferably from about 2000 g/m<sup>2</sup>/24 hr. to about 5000 g/m<sup>2</sup>/24 hr.

The moisture vapor transmission rate is measured by the method set forth below. A known amount of CaCl<sub>2</sub> is put into a flanged cup. A sample material is placed on top of the cup and held securely by a retaining ring and gasket. The assembly is then weighed and recorded as the initial weight. The assembly is placed in a constant temperature (40°C) and humidity (75% RH) chamber for five (5) hours. The assembly is then removed from the chamber and allowed to equilibrate for at least 30 minutes at the temperature of the room where the balance is located. The assembly is then weighed and recorded as the final weight. The moisture vapor transmission rate is calculated and expressed in g/m<sup>2</sup>/24 hr using the following formula:



$$\text{MVTR} = \frac{(\text{final weight} - \text{initial weight}) \times 24.0}{\text{area of sample in meters} \times 5.0 (\text{time in chamber})}$$

Another measurement of breathability is the oxygen permeation rate (OPR) of the material. In order to reduce humidity and heat buildup within the diaper, it has been found that the breathable film of the present invention when used as a backsheet on a disposable diaper should have a oxygen permeation rate of from about 3 cu. meters/sq. meter/24 hrs. to about 20 cu. meters/sq. meter/24 hrs.

The oxygen permeation rate is measured by the method set forth below. The rate of oxygen permeation through a material is measured using a glass chamber with an oxygen monitor and probe. A sample is cut approximately equal in diameter to an aluminum foil disc having a 12 cm diameter, Mocon Part #025-493. The sample is placed on top of the disc. The glass chamber is placed on the disc and a circle is traced. The circle in the sample is cut. Once prepared, the sample disc (foil side down) is clamped between the glass chamber containing the probe and the center glass piece. A circular piece of rubber is placed between the center glass piece and the open ended glass chamber and sealed with a second clamp. The chamber is flushed with nitrogen to a concentration of 0.1% oxygen on both sides of the film. One side is then exposed to air (20.9% oxygen), and the times required to reach predetermined oxygen concentrations on the opposite side of the film are recorded. The permeation rate of oxygen through the sample is then calculated using the following formula:

$$\text{OPR} = \frac{(5.57 \times 10^4)(\text{volume (mL)})}{(\text{average time (sec)})}$$

Where:

$(5.57 \times 10^4)$  = Constant value incorporating the slope (time in minutes vs % oxygen level change (0.5%)), 1% oxygen level of interest, conversion of seconds to minutes, conversion of minutes to days and surface area of sample ( $0.775 \text{ in}^2$ );

Volume = Measured volume of the glass chamber containing the oxygen probe;

Average time = Average value of the time interval associated with a 0.5% increase in oxygen concentration.

Prior to undergoing the process of the present invention the blended film has a moisture vapor transmission rate of less than about  $100 \text{ g/m}^2/24 \text{ hr.}$  and an oxygen permeation rate of less than about  $0.5 \text{ cu. meters/sq. meter/24 hrs.}$  Thus blended film

does not provide the desired breathability achieved by the film after having undergone the process of the present invention.

As seen in Figs 3A and 4, the method of the present invention expands the film out of the x-y plane, i.e., in the z direction to provide the film with an increased caliper via the raised rib-like elements. In contrast, traditional incremental stretching equipment, such as disclosed in U.S. Pat. No. 4,116,892 issued to Schwarz on Sep. 26, 1978, expands the film in the x-y plane, in either the longitudinal or transverse directions or both. Thus, traditional incremental stretching equipment produces a film of larger planar dimension, e.g., a film having a larger width and/or length dimension. Producing a film of larger dimension may be undesirable in certain circumstances as this may require modifying existing production equipment to handle the larger film.

In addition to providing the film with breathability, the process of the present invention provides a film having a cloth-like appearance. This is particularly important if the film is to be used as a backsheet on a disposable diaper. Furthermore, the present invention may also provide the breathable film with elastic-like properties allowing the film to stretch under relatively low forces. The ability to stretch under normal wearing forces can be very beneficial for disposable diapers to provide increased comfort and improved fit for the wearer.

As opposed to being unwound from a supply roll as shown in Fig. 1, the film 12 may be fed through the nip 51 of opposing rolls 52 and 54 without first being stored on a supply roll. For example, the film 12 may be fed through the nip 51 directly from an extruder.

After the film 12 has been fed through the nip 51 of opposing rolls 52 and 54 the film 12 may be wound up onto a take-up roll. Alternatively, the film may be fed directly to a disposable absorbent article converter where it forms the backsheet of a disposable absorbent article.

Examples of disposable absorbent articles are described in U.S. Pat. No. 4,950,264, issued to Osborn on Aug. 21, 1990; U.S. Pat. No. 4,425,130, issued to DesMarais on Jan. 10, 1984; U.S. Pat. No. 4,321,924, issued to Ahr on Mar. 30, 1982; U.S. Pat. No. 4,589,876, issued to Van Tilburg on Aug. 18, 1987; U.S. Pat. No. 3,860,003, issued to Kenneth B. Buell on Jan. 14, 1975; and U.S. Pat. No. 5,151,092 issued to Kenneth B. Buell et al. on Sept. 29, 1992. Each of these patents are hereby incorporated herein by reference.

While the entire portion of the film may be subjected to the forming operation, the present invention may also be practiced by subjecting to formation only a portion thereof. For example, it may be desirable to provide specific portions the diaper

backsheet with breathability, such as the side portions while leaving other portions, such as the central portion of the backsheet nonbreathable.

After being formed as described above, the breathable film of the present invention may be secured to other materials to form a laminate. Preferably, the  
5 breathable film of the present invention is secured to a nonwoven web. The nonwoven web may comprise natural fibers (e.g., cotton or wood fibers), or may comprise synthetic fibers such as polyethylene, polypropylene, polyester, or any combination of such fibers. The nonwoven web may be carded, spunmelt, meltblown, or air-through bonded, or have any other characteristic or be manufactured in any manner known in  
10 the art. Nonwoven webs are preferred when the laminate is to be used as a diaper backsheet as the nonwoven web forms the outermost cover of the diaper providing the diaper with a cloth-like look and feel. Further, the outer nonwoven web cover may provide the diaper with a landing zone capable of engaging the hooks of a hook and loop type fastener. Other embodiments are contemplated wherein the breathable film is  
15 secured to other materials such as woven webs, foams, scrims, films, loose fibers, or any other material or combination that will give the diaper a cloth-like look and feel.

The laminates may be made by any number of methods known to those skilled in the art. Such bonding methods include but are not limited to heat bonds, adhesive bonds (using any of a number of adhesives including but not limited to spray adhesives,  
20 hot melt adhesives, latex based adhesives and the like), pressure bonds, ultrasonic bonds, dynamic mechanical bonds, sonic bonds, or any other suitable attachment technique or combinations of these attachment techniques as are known in the art.

Alternatively, the blended film may first be secured to another material to form a laminate prior to being formed according to the method of the present invention as  
25 described above. The laminate may comprise any of the aforementioned structures. In an especially preferred embodiment, the laminate is formed by extruding the breathable blend onto a nonwoven web. The blended film is extruded directly onto a nonwoven web while still in a partially molten state, thereby bonding the blended film to one side of the nonwoven web. The laminate may then be subjected to the process of the  
30 present invention. Alternatively, the laminate may be formed by vacuum laminating a nonwoven web to the breathable blend. The laminate may then be subjected to the process of the present invention.

Referring now to Fig. 5 there is shown an illustration of an alternative embodiment of the opposing pairs of rolls of the process of Fig. 1. From the supply  
35 roll 11 the film 12 is fed through a nip 151 of a pair of opposing rolls 152 and 154 of apparatus 150. Roll 152 comprises a plurality of toothed regions 156 and grooved regions 158 extending about the circumference of the roll. The toothed regions 156

include a plurality of teeth 157. Teeth 157 are substantially parallel to the axis of roll 152. Roll 154 comprises a plurality of teeth 161 extending about the circumference of the roll. Teeth 161 are substantially parallel to the axis of roll 154. Teeth 157 of roll 152 engage or intermesh with teeth 161 of roll 154. The portions of the film 12 passing between the grooved regions 158 of roll 152 and the teeth 161 of roll 154 will be unformed, i.e., the film 12 will not be formed or stretched and will remain substantially planar, while the portions of the film passing between toothed regions 156 comprising teeth 157 and the teeth 161 of roll 154 will be formed and/or stretched producing rib-like elements in the film.

Referring now to Fig. 6 there is shown an illustration of an alternative embodiment of the opposing pairs of rolls of the process of Fig. 1. From the supply roll 11 the film 12 is fed through a nip 251 of a pair of opposing rolls 252 and 254 of apparatus 250. Roll 252 comprises a plurality of toothed regions 256 and grooved regions 258 that extend parallel to the axis of roll 252. The toothed regions 256 include a plurality of teeth 257. Teeth 257 are substantially perpendicular to the axis of roll 252. Roll 254 comprises a plurality of teeth 261 extending about the circumference of the roll. Teeth 261 are substantially perpendicular to the axis of roll 254. Teeth 257 of roll 252 engage or intermesh with teeth 261 of roll 254. The portions of the film 12 passing between the grooved regions 258 of roll 252 and the teeth 261 of roll 254 will be unformed, i.e., the film 12 will not be formed or stretched and will remain substantially planar, while the portions of the film passing between toothed regions 256 comprising teeth 257 and the teeth 261 of roll 254 will be formed and/or stretched producing rib-like elements in the film.

Fig. 7 is a schematic illustration of an alternative process for forming the breathable film of the present invention. According to the present invention, a film 312 is unwound from supply roll 311 and travels in the direction indicated by the arrows associated therewith as the supply roll 311 rotates in the direction indicated by the arrows associated therewith. The film 312 comprises a blend of a thermoplastic polymer with an inorganic material. From the supply roll 311 the film 312 is fed through a nip 351 of a pair of opposing rolls 352 and 354 of apparatus 350. The opposing rolls 352 and 354 may be any one of those shown in any one of Figs. 2, 5 or 6. After having been formed by apparatus 350 the film 312 is fed through a nip of a pair of opposing rolls 452 and 454 of apparatus 450. The opposing rolls 452 and 454 may be any one of those shown in any one of Figs. 2, 5 or 6.

The above sequence may be repeated any number of times until the desired properties are obtained. Furthermore, the degree of engagement of opposing rolls, the

dimension, shape and spacing of the teeth on the opposing rolls, and the size of the rolls can be chosen to produce the desired properties.

5 In an alternative embodiment, the process of the present invention may be practiced in combination with the incremental stretching operation disclosed in the aforementioned U.S. Pat. No. 4,116,892 issued to Schwarz on Sep. 26, 1978, which is incorporated herein by reference. For example, the film may be incrementally stretched as disclosed in Schwarz and then fed through the opposing rolls of the present invention. The above sequence may be reversed and/or repeated to produce the desired properties in the film.

10 While particular embodiments of the present invention have been illustrated and described, it would be obvious to those skilled in the art that various other changes and modifications can be made without departing from the spirit and scope of the invention. It is therefore intended to cover in the appended claims all such changes and modifications that are within the scope of this invention.

**WHAT IS CLAIMED IS:**

1. A method for forming a breathable film, the film comprising a blend of a thermoplastic polymer with an inorganic material characterized in that;
  - a) the film is fed between a first roll and a second roll, said first roll comprising a plurality of toothed regions spaced apart by a plurality of grooved regions, said toothed regions comprising a plurality of teeth, said second roll comprising a plurality of teeth which mesh with said teeth on said first roll, as said film is fed between said first roll and said second roll the portion of said film passing between the grooved regions on said first roll and the teeth on said second roll remains substantially planar forming first regions in said film while the portion of said film passing between the teeth on said first roll and the teeth on said second roll being formed into second regions having raised rib-like elements.
2. The method of Claim 1, wherein said first region and said second region are visually distinct from one another.
3. The method of either Claim 1 or Claim 2, wherein said first region is free of said rib-like elements.
4. The method of any one of the preceding claims wherein said film forms a backsheet on a disposable absorbent article.
5. The method of any one of the preceding claims wherein said film forms a portion of a backsheet on a disposable absorbent article.
6. The method of any one of the preceding claims, additionally comprising the step of:
  - b) joining said film to a nonwoven web.
7. The method of Claim 1, wherein said film is joined to a nonwoven web to form a laminate prior to step a).

8. The method of Claim 7, wherein said film is joined to said nonwoven web by extruding said film onto said nonwoven web.
9. The method of any one of the preceding claims wherein said inorganic material comprises calcium carbonate.
10. A method of Claim 1 additionally comprising the step of:
  - b) feeding said film between a third roll and a fourth roll, said third roll comprising a plurality of toothed regions spaced apart by a plurality of grooved regions, said toothed regions comprising a plurality of teeth which are substantially parallel to the axis of said third roll, said fourth roll comprising a plurality of teeth which mesh with said teeth of said third roll, said teeth of said fourth roll are substantially parallel to the axis of said fourth roll.

1/8




Fig. 1




Fig. 2



2/8




Fig. 3

3/8




Fig. 3A

4/8




Fig. 4

5/8




Fig. 4A

6/8




Fig. 4B

7/8




Fig. 5

8/8




Fig. 6




Fig. 7

# INTERNATIONAL SEARCH REPORT

II. International Application No

PCT/IB 98/00663

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B29C55/18

According to International Patent Classification(IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 91 12125 A (CLOPAY CORP) 22 August 1991 see page 6, line 1 - line 22 see page 8, line 17 - line 25 ---	1-10
A	EP 0 338 747 A (RASMUSSEN O B) 25 October 1989 see page 10, line 20 - line 25; figures 1-3,5A,5B ---	1-10
A	EP 0 350 034 A (GRUBER BRUNO) 10 January 1990 see column 6, line 5 - line 13; figure 9 ---	1-10
A	US 5 518 801 A (CHAPPELL CHARLES W ET AL) 21 May 1996 cited in the application see figures 5,5A,36,37 -----	1-10

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

24 June 1998

Date of mailing of the international search report

30/07/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Attalla, G



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 98/00663

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9112125 A	22-08-1991	AT 106314 T	15-06-1994
		AU 642981 B	04-11-1993
		AU 7304691 A	03-09-1991
		CA 2075940 A,C	13-08-1991
		DE 69102267 D	07-07-1994
		DE 69102267 T	15-09-1994
		DK 515501 T	10-10-1994
		EP 0515501 A	02-12-1992
		ES 2055593 T	16-08-1994
		IE 68677 B	10-07-1996
		JP 7045174 B	17-05-1995
		JP 5505149 T	05-08-1993
		US 5202173 A	13-04-1993
		US 5296184 A	22-03-1994
		US 5254111 A	19-10-1993
EP 0338747 A	25-10-1989	AT 130566 T	15-12-1995
		AU 637047 B	20-05-1993
		AU 3444689 A	24-11-1989
		CA 1332024 A	20-09-1994
		CN 1038786 A,B	17-01-1990
		DE 68924865 D	04-01-1996
		DE 68924865 T	14-11-1996
		DK 250590 A	17-12-1990
		EP 0411007 A	06-02-1991
		EP 0665161 A	02-08-1995
		ES 2082773 T	01-04-1996
		WO 8910312 A	02-11-1989
		IE 72159 B	26-03-1997
		JP 2632583 B	23-07-1997
		JP 3505184 T	14-11-1991
		MX 169245 B	25-06-1993
		NO 302876 B	04-05-1998
		PT 90306 A,B	10-11-1989
		RU 2050310 C	20-12-1995
		US 5205650 A	27-04-1993
		US 5330133 A	19-07-1994
EP 0350034 A	10-01-1990	DE 3922257 A	11-01-1990

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IB 98/00663

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5518801 A	21-05-1996	AU 7370294 A	28-02-1995
		BR 9407220 A	17-09-1996
		CA 2168771 A	09-02-1995
		CN 1132471 A	02-10-1996
		CZ 9600307 A	17-07-1996
		EP 0712304 A	22-05-1996
		FI 960495 A	02-04-1996
		HU 73593 A	28-08-1996
		JP 9501847 T	25-02-1997
		NO 960424 A	02-04-1996
		WO 9503765 A	09-02-1995
		US 5691035 A	25-11-1997
		US 5723087 A	03-03-1998

---